

WOODSAFE®

1.03.Pine Declaration of Performance Woodsafe PRO Pine panel open Surface treat

<i>Document name</i> 1.03.Pine Declaration of Performance Woodsafe PRO Pine panel open Surface treat	<i>Governing document</i> CPR305/2011, EN14915:2013 0402-CPR-SC0243-09	<i>Language / Språk</i> English	<i>Number of pages DoP</i> 3
<i>Fire impregnation system</i> WOODSAFE® PRO™	<i>Description</i> Fire impregnation for wooden panels	<i>Version</i> 1	<i>Product code</i> 03.Pine
<i>Compiled by</i> Peter Johnson, CPO peter.johnson@woodsafes.com		<i>Supersedes version</i>	
<i>Approved by</i> Thomas Bengtsson, CEO thomas.bengtsson@woodsafes.com.		<i>Date</i> 2025-03-11	

1. Product group

WOODSAFE® PRO Pine panel open Surface treat, in thickness min 18mm.

2. Construction product identification

Fire protection system:	WOODSAFE® PRO, fire impregnation
Wood treatment:	-
Wood specie and product type:	Pine panel open
Surface treatment:	Alt 1: Painted with surface coating called "Teknos Firestain". Coating applied by paint brush machine with grinding between first and second layer. First layer applied to all sides of panel. Second layer to face of panel. Total applied wet amount of coating 10 m2/l.
Product code:	03.Pine

Sawn, planed and profiled wooden panels that meet the requirements according to EN14915:2013. Fire protection impregnated according to system Woodsafe PRO. For more information, see page 2 of this Declaration of performance as well as package specification and associated document.

3. The products intended end use/uses

Exterior wooden panel as cladding with material properties against fire.

4. Manufacturer

Business:	Woodsafe Timber Protection AB with place of manufacture, Fågelbacken brandövningsplats, 72595 Västerås, Sverige.
VAT:	SE556630532101
Phone:	010-206 72 30. Technical support 010-206 72 37.
E-mail:	kundtjanst@woodsafes.com
Website:	www.woodsafes.com
Registered trademark:	WOODSAFE® PRO™

5. System for assessment and continuous control of the construction product's performance, system 1

System 1 for reaction to fire and system 4 for other properties. Production is carried out, controlled and operated by the quality system WQS (Woodsafe Quality System). The quality system ensures that the performance of the manufactured products complies with the characteristics declared in this performance declaration.

6. Declared performance in accordance with harmonized standard and notified body

Fire classification

- EN13501-1

Harmonized product standard wood panels

- EN14915:2013

Control body for continuous manufacturing control

- RISE No.0402 Control agreement number 210-09-0082, Rev. 2024-04-11
- Control of continuity of product performance according to system 1 and has issued attestation of continuity of product performance.

WOODSAFE®

1.03.Pine Declaration of Performance Woodsafe PRO Pine panel open Surface treat

7. Stated performance

Essential properties	Performance				
Reaction to fire	Fire class	B-s1,d0 at 18mm thickness. B-s2,d0 at >18mm thickness Classified according to EN13501-1			
	Joints	Horizontal and vertical			
	Installation (1,2,3,4)	1 – Assembly: Horizontal – Vertical – OK with max 10mm gap between panels Mechanically attached 2 – With or without an air gap to the substrate 3 – All substrates with Euroclass A1 or A2s1,d0 with minimum thickness 12mm and density min 525 kg/m3. 4 – NPD			
		Horizontal installation		Vertical installation	
				Yes	
	Battens (2)	Optional: Fire impregnated wooden battens			
	Substrate (3)	Density	Minimum thickness	Fire class EN13501-1	Fire class for wood-based substrates EN13501-1
		Min 525 kg/m ³	12mm	A1, d0 or A2s1, d0	-
Release of formaldehyde	NPD				
Pentachlorophenol content	None				
Vapor permeability	NPD				
Sound absorption	NPD				

Use class	Area of use			Additional information
EN16755	INT1 Normal dry interior	INT2 Varying moist interior	EXT Damp interior and exterior environment	The fire retardant is approved for exterior exposure with surface treatment requirements. Can also be used in an interior environment without surface treatment. Approval is confirmed in a separate type approval certificate.

Intended use	Exterior
Panel type	Fire protection impregnated cladding
Wood specie	PNSY (pine)
Density	400-600 kg/m ³
Fastening	Galvanized screw or nail

8. REACH: SVHC (Substances of Very High Concern)

WOODSAFE® PRO is consistent with both REACH Regulation (EC) 1907/2006 and the Biocidal Products Regulation (EU) 528/2012. PRO does not contain any prohibited chemicals according to REACH. Some substances may be on the SVHC list according to CLP regulations, but as a final product and using fire retardant treated wood, Woodsafe PRO is not classified as hazardous to health or the environment.

9. Associated documents

Associated documents for the product are available at www.woodsafepro.com/en/document-library

Västerås 2025-03-11
Woodsafe Timber Protection AB



Thomas Bengtsson, CEO

WOODSAFE®